

ANTISTATIC AND TEAR RESISTANT CF106-2 AS

CF106-2 AS is a dimensionally stable Premium Grade VERSIV™ PTFE-coated glasscloth with an anti-static coating. It has a very high PTFE content and is specifically coated in order to provide an extremely smooth surface with good wear characteristics.

Previously known as **CF 100-6 AS, CHEMFAB® CF106-2 AS*



FEATURES AND BENEFITS

- Chemically inert
- Non-stick and washable
- Thermally stable from -150 to +260 °C
- Non-flammable/fire resistant
- Excellent heat transfer
- Dimensionally stable
- Low electrical losses

AVAILABILITY

- Available in widths up to 2000 mm

*Pictures shown are for illustration purpose only.



TYPICAL PROPERTIES

Property	Value	Unit	Test Method
Standard Widths	1000, 1525, 2000	mm	-
Weight	315	g/m ²	FTMS 191A-5041
Thickness	0.145	mm	FTMS 191A-5030
Tensile Strength	300 x 300	N/cm	FTMS 191A-5102
Trap Tear Strength	15 x 15	N	FTMS 191A-5136
Surface Strength	<1 x 10 ⁶	Ω/sq	ASTM D257-78
Temperature Resistance	-150 to +260	°C	-
PTFE Content	67	%	-

The values presented are typical values and should not be used for specification purposes. Contact your Saint-Gobain Composite Solutions representative for more information.

CONTACT SAINT-GOBAIN COMPOSITE SOLUTIONS



Ireland
Kilrush Business Park,
Kilrush, Co. Clare, V15 NW27
Tel: +353 65 90 80 170

Poland
Tel: +48 (63) 261 7252

compositesolutions-saint-gobain.com

IMPORTANT: The values presented are typical values and should not be used for specification purposes. Contact your representative for more information. It is the user's responsibility to ensure the suitability and safety of Saint-Gobain Composite Solutions products for all intended uses and that the materials to be used comply with all applicable regulatory requirements. Saint-Gobain assumes no responsibility for any product failures that occur due to misuse of the materials it provides arising out of the design, fabrication or application of the products into which the materials are incorporated by purchaser and/or user.

WARRANTY: We warranty specifications at delivery and honor claims for such breach of warranty for six (6) months after delivery. The only obligation under any applicable product warranty will be to replace any portion proving defective, or at our option, to refund the purchase price thereof. User assumes all other risks, if any, including the risk of injury, loss or damage, whether direct or consequential arising out of the use, misuse or inability to use this product(s). SAINT-GOBAIN COMPOSITE SOLUTIONS DISCLAIMS ALL IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.

© Saint-Gobain Composite Solutions 2022 | Versiv and Saint-Gobain Composite Solutions are trademarks of Saint-Gobain.

Valid 10/2022 • Supersedes all previous versions

VS.PDS.CF106-2AS.EU.EN.V1

